

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁷ : A61L 24/10, 27/22, A61K 38/10, 38/17	A1	(11) International Publication Number: WO 00/01427 (43) International Publication Date: 13 January 2000 (13.01.00)
(21) International Application Number: PCT/NL99/00417 (22) International Filing Date: 2 July 1999 (02.07.99) (30) Priority Data: 98202233.7 2 July 1998 (02.07.98) EP (71) Applicant (for all designated States except US): STICHTING SKELETAL TISSUE ENGINEERING GROUP AMSTERDAM [NL/NL]; c/o Academisch Ziekenhuis Vrije Universiteit, De Boelelaan 1117, NL-1081 HV Amsterdam (NL). (72) Inventors; and (75) Inventors/Applicants (for US only): BURGER, Elisabeth, Henriëtte [NL/NL]; Korteraarseweg 107, NL-2461 GK Ter Aar (NL). VAN NIEUW AMERONGEN, Arie [NL/NL]; G. van Nijenrodestraat 136, NL-3621 GK Breukelen (NL). WUISMAN, Paulus, Ignatius, Jozef, Maria [NL/NL]; Lupine Oord 29, NL-3991 VG Houten (NL). (74) Agent: VAN SOMEREN, Petronella, Francisca, Hendrika, Maria; Arnold & Siedsma, Sweelinckplein 1, NL-2517 GK The Hague (NL).		(81) Designated States: AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i> <i>In English translation (filed in Dutch).</i>
(54) Title: BONE CEMENT WITH ANTIMICROBIAL PEPTIDES (57) Abstract The invention relates to bone material for the prevention and treatment of osteomyelitis, which material is provided with antimicrobial peptides (AMPs) consisting of an amino acid chain which contains a domain of 10 to 25 amino acids, wherein the majority of the amino acids of the one half of the domain are positively charged amino acids and the majority of the amino acids of the other half of the domain are uncharged amino acids, which AMPs can be released to the surrounding area for a period of time and wherein the bone material forms bone cement after curing and the AMPs are distributed homogeneously in the cured bone cement. The invention further relates to a method of manufacturing the bone material, wherein the bone material is cured to bone cement and wherein the AMPs are distributed homogeneously in the cured bone cement.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

BONE CEMENT WITH ANTIMICROBIAL PEPTIDES

The invention relates to the use of antimicrobial peptides (AMP) in calcium phosphate bone cement and forms a system which provides for slow release of the AMP for prevention and treatment of infections of the bone
5 (osteomyelitis) and the surrounding soft tissues.

Preventing infections of the soft tissues and the bone after operations remains a cause for concern in orthopaedic and trauma surgery. Infection of bone tissues (osteomyelitis) and/or the surrounding soft tissue is
10 very difficult to cure and this is a reason why stringent prevention is required. At this moment granules of polymethyl methacrylate (PMMA-granules) are used for this purpose. When they are placed in the surgical wound they function as a slow release system for obtaining high
15 local concentrations of antibiotics, while the systemic concentrations remain low. Such granules are however non-re-absorbable and an additional operation is therefore necessary. The intensive use of antibiotics in human and veterinary medicine has further resulted in large scale
20 resistance of bacteria and fungi to antibiotics such as gentamicin. New therapies for prevention and treatment of for instance osteomyelitis are therefore urgently required.

The present invention provides for this purpose a
25 new system for the prevention and treatment of osteomyelitis, which makes use of a re-absorbable calcium phosphate cement carrier and a new class of antibiotic agents, the so-called antimicrobial peptides (AMPs).

The AMPs used in the invention are peptides
30 consisting of an amino acid chain which contains a domain of 10 to 25 amino acids, wherein the majority of the amino acids of the one half of the domain are positively

charged amino acids and the majority of the other half of the domain are uncharged amino acids.

The structure of these peptides has a number of variations. Firstly, the domain can form an α -helix, of which at least a majority of the positions 1, 2, 5, 6, 9 (12, 13, 16, 19, 20, 23 and 24) contains a positively charged amino acid, position 8 is a positive or an uncharged amino acid and at least a majority of the positions 3, 4, 7, 10, (11, 14, 15, 17, 18, 21, 22, 25) contains an uncharged amino acid. These peptides have a lateral amphipathicity, i.e. a maximum hydrophobic moment at 100°. Stated simply, these peptides are hydrophobic on the left side and hydrophilic on the right side or vice versa. These peptides are referred to herein as "type I".

The domain can further form an α -helix, of which at least a majority of the positions 1, 2, 5, 6, 9 (12, 13, 16, 19, 20, 23 and 24) contains an uncharged amino acid, position 8 is a positive or an uncharged amino acid and at least a majority of the positions 3, 4, 7, 10, (11, 14, 15, 17, 18, 21, 22, 25) contains a positively charged amino acid. These peptides have a lateral amphipathicity, i.e. a maximum hydrophobic moment at 100°. Stated simply, these peptides are hydrophobic on the right side and hydrophilic on the left side or vice versa. These peptides are designated "type II" herein and are in principle mirror-symmetrical to type I peptides.

In addition, the domain can form an α -helix, wherein at least a majority of the positions 1 to 6 (or 7 or 8 or 9 or 10 or 11 or 12) contains an uncharged amino acid and a positively charged amino acid is found at position 7 (or 8 or 9 or 10 or 11 or 12 or 13) to 25. These peptides have a longitudinal amphipathicity, i.e. a minimum hydrophobic moment at 100°. These peptides are hydrophobic on their "top" and hydrophilic on their "bottom". Such peptides are designated "type III".

Conversely, the domain can form an α -helix, wherein at least a majority of the positions 1 to 6 (or 7 or 8 or 9 or 10 or 11 or 12) contains a positively charged amino acid and an uncharged amino acid is found at position 7 (or 8 or 9 or 10 or 11 or 12 or 13) to 25. These peptides likewise have a longitudinal amphipathicity and therefore a minimum hydrophobic moment at 100° . These peptides are hydrophobic on their "bottom" and hydrophilic on their "top". Such peptides are designated "type IV".

Finally, the domain can form a so-called β -strand and contain a positively charged amino acid on at least a majority of the positions 1, 3, 5, 7, 9 (11, 13, 15, 17, 19, 21, 23 and 25) and an uncharged amino acid on at least a majority of the positions 2, 4, 6, 8, 10, (12, 14, 16, 18, 20, 22, 24). Such a β -strand is laterally amphipathic and has a maximum hydrophobic moment at 180° . The β -strand structure is flatter than the α -helix and, stated simply, is hydrophobic on the left and hydrophilic on the right or vice versa. These are "type V" peptides.

The positively charged amino acids are preferably chosen from the group consisting of ornithine (O), lysine (K), arginine (R) and histidine (H), while the uncharged amino acids are preferably chosen from the group consisting of the aliphatic amino acids glycine (G), alanine (A), valine (V), leucine (L), isoleucine (I), the amino acids with a dipolar side chain methionine (M), asparagine (N), glutamine (Q), serine (S), threonine (T), the amino acids with an aromatic side chain phenylalanine (F), tyrosine (Y), tryptophan (W). Amino acids on the border between hydrophilic and hydrophobic can be chosen from both groups or from the remaining amino acids.

Hardly any difference in activity can in principle be detected when one of the positive amino acids and/or one of the uncharged amino acids is replaced by a random amino acid. The majority of the positively charged amino acids is therefore preferably the total number of

positively charged amino acids minus 1 and the majority of the uncharged amino acids is preferably the total number of uncharged amino acids minus 1.

The domain can be a part of a larger peptide but can itself also make up the entire peptide. When the domain forms part of a larger peptide, the C-terminal and/or N-terminal amino acids which are then additionally present can be random amino acids.

The following peptides of the type I are particularly recommended:

	KRLFKEKLFSLRKY	(peptide 3)
	KRLFKELLFSLRKY	(peptide 4)
	KRLFKEKKSLRKY	(peptide 5)
	KRLFKELLKSLRKY	(peptide 6)
15	OOLFOELOOSLOOY	(peptide 7)
	OOLFOELLOSLOOY	(peptide 8)
	KRLFKKLKFSLRKY	(peptide 9)
	KRLFKKLLFSLRKY	(peptide 10)

A preferred peptide of the type III has the following amino acid sequence:

LLLFLKKRKKRKY (peptide 11)

The peptides according to the invention can also contain further modifications. These modifications are for instance an N-terminal amide ring, for instance with acetic acid anhydride, or an alternative cleavage of the synthesis resin by which the C-terminus is modified. For this latter a replacement of the C-terminal carboxylic acid group by an amide, ester, ketone, aldehyde or alcohol group can be envisaged. Peptides with such a modification are for instance:

KRLFKEKLFSLRKY-amide (peptide 12)

KRLFKELLFSLRKY-amide (peptide 13)

In addition to single peptides, oligomers can also be made. These are preferably linear oligomers of the peptides according to the invention. The coupling can be head-to-head and tail-to-tail as well as head-to-tail,

either by direct synthesis or by post-synthetic enzymatic coupling. For a trans-membrane pore formation a minimum peptide length is required. Oligomers of the peptides according to the invention are double length and thereby better able in principle to span the whole phospholipid double layer of the bacterial cell membrane at one time. The activity of the peptide could hereby improve even further. In addition, extension of the peptides provides stabilisation of the helix conformation. A spacer must usually be inserted. In direct synthesis of head-to-tail coupled oligomers a spacer can be inserted to size by the use of a chain of unnatural amino acids of the correct length, for instance β -alanine, γ -amino butyric acid, ϵ -amino caproic acid, etc. Heterodifunctional coupling reagents, such as are commercially available for coupling peptide antigens to carrier proteins (for instance 1-ethyl-3-[3-dimethylaminopropyl]carbodiimide (EDC), *m*-maleimidobenzoyl)-*N*-hydroxysuccinimide ester (MBS), *N*-succinimidyl 3-[pyridyldithio]propionate (SPDD) etc.) are used to make linear oligomers with an inserted spacer. For head-to-head and tail-to-tail couplings can be used trivalent amino acids such as asparagine acid (D), glutamine acid (E), ornithine (O), lysine (K), serine (S), cysteine. Such oligomers are for instance:

25	KRKFHEKHHSRGYC-CYGRHSHHKEHFKRK	(peptide 14)
	YGRHSHHKEHFKRKC-CKRKFHEKHHSRGY	(peptide 15)
	$^{\alpha}\text{N}, ^{\epsilon}\text{N}-(\text{KRKFHEKHHSRGY})_2\text{K-amide}$	(peptide 16)
	$^{\alpha}\text{N}, ^{\epsilon}\text{N}-(\text{KRLFKEKLFSLRKY})_2\text{K-amide}$	(peptide 17)
	$^{\alpha}\text{N}, ^{\epsilon}\text{N}-(\text{KRLFKKLKFSLRKY})_2\text{K-amide}$	(peptide 18)

Peptides 14 and 15 are obtained by synthesis of peptide 2 with an additional C-terminal respectively N-terminal cysteine, whereafter the oligomer is obtained by air oxidation. Peptides 16, 17 and 18 are obtained by making use of the Multiple Antigenic Peptide (MAP) strategy, wherein a lysine having on both the α - and on the ϵ -amino group an Fmoc protection was used as first amino acid on

the synthesis resin, whereby two identical amino acid chains (peptides 2, 3 and 9) were synthesized simultaneously on one lysine molecule.

The peptides described herein have no or hardly any haemolytic activity in physiological buffers such as PBS (phosphate-buffered saline solution). A low activity against erythrocytes of human origin is an indication of low toxicity. This selectivity is essential for the use of these peptides as antibiotics.

10 The peptides have a wide spectrum of antibacterial and antifungal activity, even against methycillin-resistant Staphylococcus aureus (MRSA), Pseudomonas aeruginosa (which is particularly dangerous in the case of osteomyelitis) and amphotericin-B-resistant Candida
15 albicans.

The invention further makes use of bone material which after curing forms bone cement and wherein the AMPs are distributed homogeneously in the cured bone cement. It is biocompatible, re-absorbable and inert, and forms
20 at body temperature. The final cement moreover has sufficient strength and stiffness to serve as bone replacement.

It has been found according to the invention that the inclusion of the AMPs in the cement does not affect
25 the mechanical properties thereof.

In order to include the AMPs in the cement, they are dissolved in a liquid medium, preferably water, and mixed with the bone material before or after curing thereof.

A blood protein-containing solution, in particular
30 albumin, is preferably used to hold the AMPs in solution, in order to ensure a homogeneous distribution of the AMPs in the final cured bone cement.

In a preferred embodiment bone material contains calcium phosphate. With a view to the biocompatibility
35 this is particularly a mixture of dicalcium phosphate,

tricalcium phosphate, tetracalcium phosphate and/or hydroxyl-apatite.

The invention further relates to a method of manufacturing a bone material according to the invention, wherein the bone material is cured to bone cement and wherein the AMPs are distributed homogeneously in the cured bone cement. As stated, the AMPs are dissolved in a liquid medium, preferably water, and mixed with the bone material before or after curing thereof. The AMPs are preferably mixed with the bone material after curing. A longer release period is thus provided in which the AMPs can be released to the surrounding area after arranging of the bone material. The starting point here in each case is that the AMPs are always active only where this is necessary.

The invention also relates to a device for administering bone material provided with AMPs according to the invention, wherein provision is made for at least two compartments for separately containing the bone material and AMPs, a mixing chamber for mixing the bone material and the AMPs and a spray nozzle for spraying the mixture out of the mixing chamber.

The invention will be further elucidated with reference to a discussion of a number of tests in accordance with preferred variants of the invention, wherein the procedures for manufacturing the present bone material with added AMPs will be discussed.

1. A sterile cement powder consists of a mixture of alpha-tricalcium phosphate, tetracalcium phosphate-monoxide en dicalcium phosphate dibasic in a ratio of 75:20:5, or otherwise if desired.
2. A sterile AMP solution (solution (A)) consists of 4 mM HCl in water having dissolved therein 0.1% beef

or human serum albumin and AMPs in a concentration as required varying from $2 \times 10^{-5}\%$ to 2%.

3. A second sterile solution (solution (B)) consists of
5 water having dissolved therein 12% sodium succinate and 5% chondroitin succinate.
4. Solution (A) is mixed 1 to 1 with solution (B) under
sterile conditions.
10
5. One volume part solution (A+B) is mixed with two
volume parts cement powder under sterile conditions.
This can take place:
 - 15 a. in a dish and mixed with a spatula, whereafter the cement paste is arranged immediately in-situ in the body of the patient and there cures;
 - 20 b. via a spray with two chambers, one of which contains the cement powder and the other solution (A+B); using the spray, powder and liquid are brought together in-situ in the body, whereafter the mixture cures at this
25 location.
 - c. in a dish, mould or container, whereafter the mixture cures outside the body and is
optionally ground to a powder of the desired
30 granule size, whereafter it is arranged in the body of the patient.
6. One volume part solution B is mixed with two
volume parts cement powder under sterile
35 conditions in a dish, mould or container, whereafter the mixture cures and is ground to a

powder of the desired granule size. The cured
cement is then incubated for 1 or more hours in
solution A, whereafter the cement with absorbed
AMPs is dried and stored in dry form until it
5 is arranged in the body of the patient.

CLAIMS

1. Bone material for the prevention and treatment of osteomyelitis, which material is provided with antimicrobial peptides (AMPs) consisting of an amino acid chain which contains a domain of 10 to 25 amino acids,
5 wherein the majority of the amino acids of the one half of the domain are positively charged amino acids and the majority of the amino acids of the other half of the domain are uncharged amino acids, which AMPs can be released to the surrounding area for a period of time and
10 wherein the bone material forms bone cement after curing and the AMPs are distributed homogeneously in the cured bone cement.

2. Bone material as claimed in claim 1,
characterized in that the domain forms an α -helix and at
15 least at a majority of the positions 1, 2, 5, 6, 9 (12, 13, 16, 19, 20, 23 and 24) contains a positively charged amino acid, at position 8 a positive or an uncharged amino acid and at least at a majority of the positions 3, 4, 7, 10, (11, 14, 15, 17, 18, 21, 22, 25) contains an
20 uncharged amino acid.

3. Bone material as claimed in claim 2,
characterized in that the positively charged amino acids are chosen from the group consisting of ornithine (O), lysine (K), arginine (R) and histidine (H).

25 4. Bone material as claimed in claim 2 or 3,
characterized in that the uncharged amino acids are chosen from the group consisting of the aliphatic amino acids glycine (G), alanine (A), valine (V), leucine (L), isoleucine (I), the amino acids with a dipolar side chain
30 methionine (M), asparagine (N), glutamine (Q), serine (S), threonine (T), the amino acids with an aromatic side chain phenylalanine (F), tyrosine (Y), tryptophan (W).

5. Bone material as claimed in claims 2-4,
characterized in that the majority of the positively
charged amino acids is the total number of positively
charged amino acids minus 1.

5 6. Bone material as claimed in claims 2-5,
characterized in that the majority of the uncharged amino
acids is the total number of uncharged amino acids minus
1.

7. Bone material as claimed in claims 2-6,
10 **characterized in that** the domain makes up the entire
peptide.

8. Bone material as claimed in claims 2-7, of which
the domain has the following amino acid sequence:

KRLFKELKFSLRKY (peptide 3).

15 9. Bone material as claimed in claims 2-7, of which
the domain has the following amino acid sequence:

KRLFKELLFSLRKY (peptide 4).

10. Bone material as claimed in claims 2-7, of which
the domain has the following amino acid sequence:

20 KRLFKELKKSLRKY (peptide 5).

11. Bone material as claimed in claims 2-7, of which
the domain has the following amino acid sequence:

KRLFKELLKSLRKY (peptide 6).

12. Bone material as claimed in claims 2-7, of which
25 the domain has the following amino acid sequence:

OOLFOELOOSLOOY (peptide 7).

13. Bone material as claimed in claims 2-7, of which
the domain has the following amino acid sequence:

OOLFOELLOSLOOY (peptide 8).

30 14. Bone material as claimed in claims 2-7, of which
the domain has the following amino acid sequence:

KRLFKKLFSLRKY (peptide 9).

15. Bone material as claimed in claims 2-7, of which
the domain has the following amino acid sequence:

35 KRLFKLLFSLRKY (peptide 10).

16. Bone material as claimed in claim 1,
characterized in that the domain forms an α -helix and at
least at a majority of the positions 1 to 6 (or 7 or 8 or
9 or 10 or 11 or 12) contains an uncharged amino acid and
5 at position 7 (or 8 or 9 or 10 or 11 or 12 or 13) to 25 a
positively charged amino acid.

17. Bone material as claimed in claim 1,
characterized in that the domain forms an α -helix and at
least at a majority of the positions 1 to 6 (or 7 or 8 or
10 9 or 10 or 11 or 12) contains a positively charged amino
acid and at position 7 (or 8 or 9 or 10 or 11 or 12 or
13) to 25 an uncharged amino acid.

18. Bone material as claimed in claim 16 or 17,
characterized in that the positively charged amino acids
15 are chosen from the group consisting of ornithine (O),
lysine (K), arginine (R) and histidine (H).

19. Bone material as claimed in claim 16, 17 or 18,
characterized in that the uncharged amino acids are
chosen from the group consisting of the aliphatic amino
20 acids glycine (G), alanine (A), valine (V), leucine (L),
isoleucine (I), the amino acids with a dipolar side chain
methionine (M), asparagine (N), glutamine (Q), serine
(S), threonine (T), the amino acids with an aromatic side
chain phenylalanine (F), tyrosine (Y), tryptophan (W).

25 20. Bone material as claimed in claims 16-19,
characterized in that the majority of the positively
charged amino acids is the total number of positively
charged amino acids minus 1.

21. Bone material as claimed in claims 16-20,
30 **characterized in that** the majority of the uncharged amino
acids is the total number of uncharged amino acids minus
1.

22. Bone material as claimed in claims 16-21,
characterized in that the domain makes up the entire
35 peptide.

23. Bone material as claimed in claims 16 and 18-22, of which the domain has the following amino acid sequence:

LLLFLKKRKRKY (peptide 11).

5 24. Bone material as claimed in claim 1, **characterized in that** the domain forms a so-called β -strand and contains a positively charged amino acid on at least a majority of the positions 1, 3, 5, 7, 9 (11, 13, 15, 17, 19, 21, 23 and 25) and an uncharged amino acid on
10 at least a majority of the positions 2, 4, 6, 8, 10, (12, 14, 16, 18, 20, 22, 24).

25. Bone material as claimed in claim 24, **characterized in that** the positively charged amino acids are chosen from the group consisting of ornithine (O),
15 lysine (K), arginine (R) and histidine (H).

26. Bone material as claimed in claim 24, **characterized in that** the uncharged amino acids are chosen from the group consisting of the aliphatic amino acids glycine (G), alanine (A), valine (V), leucine (L),
20 isoleucine (I), the amino acids with a dipolar side chain methionine (M), asparagine (N), glutamine (Q), serine (S), threonine (T), the amino acids with an aromatic side chain phenylalanine (F), tyrosine (Y), tryptophan (W).

27. Bone material as claimed in claims 24-26,
25 **characterized in that** the majority of the positively charged amino acids is the total number of positively charged amino acids minus 1.

28. Bone material as claimed in claims 24-27, **characterized in that** the majority of the uncharged amino
30 acids is the total number of uncharged amino acids minus 1.

29. Bone material as claimed in claims 24-28, **characterized in that** the domain makes up the entire peptide.

30. Bone material as claimed in claims 1-29, wherein the N-terminus is amidated.

31. Bone material as claimed in claims 1-30, wherein the C-terminal carboxylic acid group is replaced by an
5 amide, ester, ketone, aldehyde or alcohol group.

32. Method of manufacturing bone material as claimed in any of the claims 1-31, wherein the bone material is cured to bone cement and wherein the AMPs are distributed homogeneously in the cured bone cement.

10 33. Method as claimed in claim 32, wherein the AMPs are dissolved in liquid medium, preferably water, and mixed with the bone material after curing thereof.

34. Method as claimed in claim 32 or 33, wherein the cured bone cement is formed to a granulate.

15

INTERNATIONAL SEARCH REPORT

International Application No

PCT/NL 99/00417

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 A61L24/10 A61L27/22 A61K38/10 A61K38/17

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 A61L

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 96 39202 A (OSTEOGENICS INC) 12 December 1996 (1996-12-12) page 44, line 4; claims ---	1,32-34
A	EP 0 510 912 A (MORINAGA MILK INDUSTRY CO LTD) 28 October 1992 (1992-10-28) claims; examples ---	1-34
A	WO 97 18827 A (INTRABIOTICS PHARMACEUTICALS I) 29 May 1997 (1997-05-29) claims; examples ---	1
A	WO 94 15653 A (GENENTECH INC) 21 July 1994 (1994-07-21) claims ---	1
	--- --/--	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

2 November 1999

Date of mailing of the international search report

16/11/1999

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

ESPINOSA, M

INTERNATIONAL SEARCH REPORT

International Application No

PCT/NL 99/00417

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	WO 94 20064 A (AMERICAN DENTAL ASS) 15 September 1994 (1994-09-15) claims; examples 1-10 ---	1, 32-34
A	DUCAN YU ET AL: "SELF-SETTING HYDROXYAPATITE CEMENT: A NOVEL SKELETAL DRUG-DELIVERY SYSTEM FOR ANTOBIOTICS" JOURNAL OF PHARMACEUTICAL SCIENCES, vol. 81, no. 6, 1 June 1992 (1992-06-01), pages 529-531, XP000271282 ISSN: 0022-3549 ---	1, 32-34
A	WO 92 01462 A (SCRIPPS RESEARCH INST) 6 February 1992 (1992-02-06) claims ---	1
E	WO 99 37678 A (HELMERHORST EVA JOSEPHINE ;NIEUW AMERONGEN ARIE VAN (NL); STICHTIN) 29 July 1999 (1999-07-29) the whole document -----	1-34

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/NL 99/00417

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 9639202 A	12-12-1996	AU 6149696 A BR 9608344 A CA 2223596 A EP 0830149 A JP 11506659 T	24-12-1996 05-01-1999 12-12-1996 25-03-1998 15-06-1999
EP 0510912 A	28-10-1992	AU 664697 B AU 1514692 A CA 2066997 A DE 69223844 D DE 69223844 T DK 510912 T JP 5148295 A NZ 242437 A US 5424396 A	30-11-1995 29-10-1992 25-10-1992 12-02-1998 16-04-1998 09-02-1998 15-06-1993 27-07-1993 13-06-1995
WO 9718827 A	29-05-1997	AU 704851 B AU 1162997 A AU 7739496 A CA 2238429 A CZ 9801591 A CZ 9801592 A EP 0862448 A EP 0865292 A HU 9901183 A NO 982310 A NO 982311 A PL 326924 A WO 9718826 A	06-05-1999 11-06-1997 11-06-1997 29-05-1997 14-10-1998 16-12-1998 09-09-1998 23-09-1998 28-07-1999 22-07-1998 22-07-1998 09-11-1998 29-05-1997
WO 9415653 A	21-07-1994	AT 153535 T AU 671721 B AU 6026294 A CA 2151486 A DE 69403439 D DE 69403439 T DK 679097 T EP 0679097 A ES 2105641 T GR 3024277 T JP 8505548 T US 5422340 A	15-06-1997 05-09-1996 15-08-1994 21-07-1994 03-07-1997 23-10-1997 22-12-1997 02-11-1995 16-10-1997 31-10-1997 18-06-1996 06-06-1995
WO 9420064 A	15-09-1994	US 5522893 A AT 183382 T AU 684722 B AU 4923993 A BR 9307825 A CA 2157890 A,C DE 69326082 D EP 0688202 A JP 8510713 T US 5542973 A US 5545254 A US 5695729 A	04-06-1996 15-09-1999 08-01-1998 26-09-1994 14-11-1995 15-09-1994 23-09-1999 27-12-1995 12-11-1996 06-08-1996 13-08-1996 09-12-1997
WO 9201462 A	06-02-1992	CA 2047317 A JP 6504260 T	20-01-1992 19-05-1994

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/NL 99/00417

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 9201462 A		US 5294605 A	15-03-1994
WO 9937678 A	29-07-1999	NONE	